

Technical Datasheet SG-8290



Beater Addition Soft Gasket Material

Material Composition

Mix of reinforced fibres with high rubber contents.

Application

It is a flexible material with high density and recovery property and can be used for soft gasket applications like oil/fuel/water pumps, carburetors, gearboxes, oil pans etc.

Color

Grey, Green, Blue (other color upon request)

Compliance

ASTM F 104 Type 7

Standard Dimensions of Material

Roll Width : 1000mm $\pm$ 50mm

Roll Weight : 50 kg (Approx.)

Available Thickness

0.40mm to 2.00mm

Operating Condition

Max. Operating Temperature : 180 °C

Technical Specifications

Typical Properties	Test Method	Typical Value	Unit
Density	ASTM F 1315	1.30 $\pm$ 0.05	g/cm ³
Compressibility at 350 kg/cm ²	ASTM F 36J	15 – 30	%
Recovery	ASTM F 36J	35 (Min.)	%
Tensile Strength	ASTM F 152	110 (Min.)	kg/cm ²
ASTM Oil No. 3/IRM 903 (5h, 150 °C)			
Thickness Increase	ASTM F 146	$\leq$ 20.0	%
Weight Increase	ASTM F 146	$\leq$ 40.0	%
ASTM Fuel B (5h, 21 °C to 30 °C)			
Thickness Increase	ASTM F 146	$\leq$ 20.0	%
Weight Increase	ASTM F 146	$\leq$ 40.0	%
In Distilled Water (5h, 21 °C to 30 °C)			
Thickness Increase	ASTM F 146	$\leq$ 20.0	%
Weight Increase	ASTM F 146	$\leq$ 40.0	%

*Size & Thickness Tolerance: $\pm$ 10%

All technical data and information are derived from years of industry experience in the production and application of sealing materials. The content is for reference purposes only and does not imply any form of warranty or guarantee. This edition supersedes earlier publications and is subject to revisions without prior notice.